

NAME	RETICULATION			PHYSICAL PROPERTIES		TECHNICAL PROPERTIES			APPLICATIVE SECTOR
	Hardener	CAT. WEIGHT (%)	Pot life (min.)	Colour A+B	Viscosity A+B (CpS)	Max Thickness (mm.)	Vitreous transmission (Tg °C)	TENSILE STRENGHT (N/mm2)	
KEMIEPOX NCT 301	EH 301	100:50	40	Transparent	600	90	48 - 52	40	Fluid, excellent mechanical resistance and smooth finish, good resistance to yellow tendency and stability, high transparence. Mounting of objects, reproduction of artistic and industrial objects, as sealant for concrete elements. If charged with mineral inert materials can be used for paving.
KEMIEPOX NCT 401	EH 401 EH 402	100:50	60 35	Transparent	500-800	100 10	45 - 50 52 - 58	40	Realization of pouring and encapsulations where it is required transparence and yellow tendency resistance.